EMI Shielding Material



Conductive Form-In-Place Gasket





MATERIAL

Conductive silicone that is cured at room temperature.




FEATURES

- Applicable for low temperature plastics
- Enhanced galvanic corrosion resistance and stability in severe environments

Force-Deflection-Resistance of F5521 Gasket

D Shape 1.0 mm(H) * 1.3 mm(W) Rate of Strain, 1.5mm/min



PROPERTIES	F5521
Elastomer Binder	Silicone
Conductive Filler	Ag/Al
Cure System	Moisture
Density	2.01 g/cm ³
Hardness	55 Shore A
Adhesion on Al Metal	>80 N/cm ²
Tensile Strength	130 psi
Tear Strength	18 Lbf/in
Operatering Temperature	-45 to 150 °C
Flammability Rating (UL94V-0)	E303387
DC-Through Resistance @ 30% Compression, 1mm H	<0.07 Ohm
Shielding Effectiveness 200 MHz ~ 40 GHz	>100 dB
Min. Bead Height	0.3 mm

GET IN TOUCH

EMAIL: SUPPORT@TENNMAX.COM

TEL: +1 360-567-0707



This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery. V1