


## Ultra-Soft Environmental Form-In-Place Gasket



## Force-Deflection of F6023 Gasket

D Shape 1.0 mm(H) \* 1.3 mm(W) Rate of Strain, 1.5mm/min

Compression Force



PROPERTIES	F6023
Composition	Silicone
Color	Black
Density	1.02 g/cm <sup>3</sup>
Softness	25 Shore A
Cure System	Moisture
Adhesion on Al Metal	>50 N/cm <sup>2</sup>
Tensile Strength	500 psi
Tear Strength	100 Lbf/in
Operatering Temperature	-45 to 150 °C
Flammability Rating (UL 94HB)	E303387
Gaskets and Seals (UL 157)	MH60623
Enclosures for Electrical Equipment, Environmental Considerations (UL 50E)	MH60623
Volume Resistivity	1 x 1014 Ohm-cm
Dielectric Strength	20 kV/mm
Minimum Bead Height	0.3 mm

## GET IN TOUCH

## EMAIL: SUPPORT@TENNMAX.COM

TEL: +1 360-567-0707

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery. V1



TENNMAX.COM